

ERKAZIT™ 7861 E**Phenolic Modified Rosin Resin****IMPORTANT CHARACTERISTICS:**

Erkazit 7861 E is especially advantageous as let down resin. This results in lower resin content and lower pigment content while maintaining the good printing properties.

APPLICATIONS:	BENEFITS:
• Publication gravure, toluene based	• Low resin content and lower pigment content while maintaining good printing properties
• Let down varnish	• Very high dilutability

Typical Properties

Property	Value	Unit	Test Method
Acid value	27	mg KOH/g	Titration
Flow time	70	sec	35% in toluene / DIN 4mm cup, 20 °C
Dilutability	160	%	Grams toluene added to 100 g solution (35%) to get 30 sec / GS 3mm cup, 20 °C
	13,4	%	Solid content to get 30 sec / GS 3mm cup, 20 °C

Updated 16/4/12 AdK

© and ™ Licensed trademarks of Lawter, Inc.

DISCLAIMER

The information provided herein was believed by Lawter, Inc. ("Lawter") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product, and to determine the suitability of the product for its intended use. All products supplied by Lawter are subject to Lawter's terms and conditions of sale. LAWTER MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY LAWTER, except that the product shall conform to Lawter's specifications. Nothing contained herein constitutes an offer for the sale of any product.