

Flex-Rez[™] 3370CS A Polyamide Resin

Description: Co-solvent soluble polyamide resin

(An overview of all products is available on request.)

100% solids

Composition: Polyamide resin

Application Field: Flexo/gravure inks for foils and plastics

Coatings and overprint varnishes

Special Properties and Good gel resistance

advantages: Adhesion with flexibility and film forming

Water, oil, grease, lard, and alkali resistance

Recommendations: Soluble in (iso-) propanol, (iso-) butanol, mixtures of alcohol with

(An overview of starting point formulations

aliphatics/aromatics

is available on request.) Preferred: aromatic solvents

NC-compatible

Typical Properties: Melting point (R&B, °C) 100

Max 6

(Test methods available on request.)

Acid value (mg

KOH/g)

Amine value (mg KOH/g) Max 6

Viscosity (40% NV Toluene/Isopropanol,

70/30, GH 25 °C) D Colour Max 10

Viscosity 40% in Toluene/IPA 70/30, 23 °C

Ford #4 46"
DIN #4 39"
Shell #5 24"
Zahn #3 39"
Dilution in Ethanol (% NV) 15

Former Name: P-3370

Updated 2/10/2011 JGC

For more information, please contact your sales or technical representative.

® and ™ Licensed trademarks of Lawter, Inc.

DISCLAIMER

The information provided herein was believed by Lawter, Inc. ("Lawter") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product, and to determine the suitability of the product for its intended use. All products supplied by Lawter are subject to Lawter's terms and conditions of sale. LAWTER MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY LAWTER, except that the product shall conform to Lawter's specifications. Nothing contained herein constitutes an offer for the sale of any product.