



Technical Data Sheet

Miraglaze™ 7017 A Non-Yellowing Heatset Overprint Varnish

IMPORTANT CHARACTERISTICS:

Miraglaze™ 7017 A is a “press ready”, high gloss, heatset overprint varnish specially formulated to be resistant to yellowing upon aging and oxidation. The balanced resin, oil and solvent system that comprises **Miraglaze 7017 A** allows the printer to print faster at lower oven temperatures. **Miraglaze 7017 A** contains a wax combination that yields prints with optimum slip and rub resistance.

APPLICATIONS:

- Overprints - heatset

BENEFITS:

- Non-yellowing
- Excellent scuff and rub resistance
- Free flow body

Typical Properties

Properties	Value	Test Method / Standard
Inkometer Tack:	6.5	1200 rpm, 1 min. @ 90°F Method PP-QC-101
% Non-Volatile:	48	Method PP-QC-105
Solvent Type:	Hydro treated	
Solvent Boiling Range:	463-535°F	
Weight/Gallon:	7.6 lbs	BAX-QC-130

Updated 2/10/2011 JGC

For more information, please contact your sales or technical representative.

® and ™ Licensed trademarks of Lawter, Inc.

DISCLAIMER

The information provided herein was believed by Lawter, Inc. (“Lawter”) to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product, and to determine the suitability of the product for its intended use. All products supplied by Lawter are subject to Lawter’s terms and conditions of sale. LAWTER MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY LAWTER, except that the product shall conform to Lawter’s specifications. Nothing contained herein constitutes an offer for the sale of any product.