

# Stirinol™ 98 A Heatset Wax Compound

### **IMPORTANT CHARACTERISTICS:**

Stirinol™ 98 A is a multi-purpose, heatset compound formulated to exhibit suitable slip and rub in heatset inks used to print publication inserts, catalogs and tabloids. Stirinol™ 98 A is easily dispersed, does not diminish gloss and has exceptional re-crystallization resistance. It can also be supplied in liquid bulk and added directly to the ink while processing.

**Stirinol™ 98 A** should be used as a direct drop in for conventional 50% solids compounds. The recommended usage level is 3 to 6%.

### **APPLICATIONS:**

- · Heatset offset ink
- Hot foil stamping
- Non-imprintable

## **BENEFITS:**

- Slip and rub for publication applications
- Exceptional re-crystallization resistance during ink processing
- Minimal effect on rheology
- Easily pumped and dispersed from drum or liquid bulk storage

# **Typical Properties**

71 1		
Properties	Value	Test Method / Standard
Grind:	N-0	NPIRI Gage units, (7% in ink)
Peppering:	N-2	NPIRI Gage units, (7% in ink)
Color:	Lt. beige	Compared to standard
Body:	Soft Paste	Compared to standard
% Non-volatile	92	Method: BAX-QC-195
Weight/Gallon:	7.3 lbs/gal	Method: BAX-QC-130

Updated 05//28/2015 JGC

For more information, please contact your sales or technical representative.

® and ™ Licensed trademarks of Lawter, Inc.

#### DISCLAIMER

The information provided herein was believed by Lawter, Inc. ("Lawter") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product, and to determine the suitability of the product for its intended use. All products supplied by Lawter are subject to Lawter's terms and conditions of sale. LAWTER MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY LAWTER, except that the product shall conform to Lawter's specifications. Nothing contained herein constitutes an offer for the sale of any product.