



Technical data sheet

SETAPRINT 2330C

Rosin Modified Resin

IMPORTANT CHARACTERISTICS:

Setaprint 2330 C is a phenolic modified rosin ester and exhibits medium solubility combined with medium viscosity in mineral distillates. The viscosity of **Setaprint 2330 C** in linseed oil is medium.

Staprint 2330 C is very suitable for combinations with other resins.

APPLICATIONS:

- Offset
- Gel and let down varnishes
- Web Offset, Heatset and Coldset
- Sheetfed inks

BENEFITS:

- Fast setting
- For high speed presses
- Low misting
- High gloss

Typical Properties

Property	Value	Unit	Test Method
Viscosity (42.5 % in Test Oil 6/9 ar blend)	25	Pa.s	Physica 23 °C, at 25 sec ⁻¹ Eurocommit
Cloud point (10 % in Test Oil 6/9)	55	°C	Eurocommit

Updated 5/18/11 TM

Former name : KRUMBHAAR 2330C

® and ™ Licensed trademarks of Lawter, Inc.

DISCLAIMER

The information provided herein was believed by Lawter, Inc. ("Lawter") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product, and to determine the suitability of the product for its intended use. All products supplied by Lawter are subject to Lawter's terms and conditions of sale. LAWTER MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY LAWTER, except that the product shall conform to Lawter's specifications. Nothing contained herein constitutes an offer for the sale of any product.