



Technical Data Sheet

Miraglaze™ 8614 A Workhorse Gloss Overprint

IMPORTANT CHARACTERISTICS:

Miraglaze™ 8614 A is a workhorse sheetfed overprint varnish formulated for maximum hardness with good tack stability. This product may be wet or dry-trapped and is suitable for commercial and folding carton applications.

Miraglaze 8614 A exhibits a very high gloss finish on thin film coverage. **Miraglaze 8614 A** also has very good rub with minimal yellowing characteristics.

Miraglaze 8614 A contains wax and ink driers to promote the formation of the necessary print properties.

APPLICATIONS:

- Overprints
- Wet or dry trapped applications

BENEFITS:

- High gloss
- Good tack stability

Typical Properties

Properties	Value	Test Method / Standard
Inkometer Tack:	6.0	400 rpm, 30" @ 90°F Method PP-QC-101
% Non-Volatile:	74	Method PP-QC-105
Acid Value:	14 max	BAX-QC-102
Solvent Boiling Range:	470-515°F	
Dry Time:	1.5 - 3.0 hours	Method PP-QC-125
Weight/Gallon:	7.7 lbs	Method PP-QC-130

Updated 2/10/2011 JGC

For more information, please contact your sales or technical representative.

® and ™ Licensed trademarks of Lawter, Inc.

DISCLAIMER

The information provided herein was believed by Lawter, Inc. ("Lawter") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product, and to determine the suitability of the product for its intended use. All products supplied by Lawter are subject to Lawter's terms and conditions of sale. LAWTER MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY LAWTER, except that the product shall conform to Lawter's specifications. Nothing contained herein constitutes an offer for the sale of any product.