

MIRAGLAZE™ 8834 E

Over print varnish

IMPORTANT CHARACTERISTICS:

Miraglaze™ 8834 E is a 60 % non-volatile over print varnish based on rosin based resins, tung oil and mineral distillate 260 – 290 °C and contains wax and driers.

Miraglaze™ 8834 E is used as over print varnish over offset inks. **Miraglaze™ 8834 E** can be applied wet-on-wet and wet-on-dry.

Miraglaze™ 8834 E exhibits good oxidative drying and very fast setting.

Miraglaze™ 8834 E exhibits good tack stability and low yellowing.

Miraglaze™ 8834 E exhibits high gloss and very good rub resistance.

APPLICATIONS:

- Offset
- Over print varnish
- Wet-on-wet, wet-on-dry

BENEFITS:

- High gloss
- Very fast drying and setting
- Good tack stability
- Very good rub resistance
- Low yellowing

Typical Properties

Property	Value	Unit	Test Method / Standard
Viscosity	12	Pa.s	Viscosity at 23°C at 25 sec ⁻¹ LIMV2
Tack	90		1 min at 85 mpm LIMV4

Updated February 21, 2011 by AdK

® and ™ Licensed trademarks of Lawter, Inc.

DISCLAIMER

The information provided herein was believed by Lawter, Inc. ("Lawter") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product, and to determine the suitability of the product for its intended use. All products supplied by Lawter are subject to Lawter's terms and conditions of sale. LAWTER MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY LAWTER, except that the product shall conform to Lawter's specifications. Nothing contained herein constitutes an offer for the sale of any product.