



Technical Data Sheet

Optilith™ 1486 A Anti-Oxidant Additive

IMPORTANT CHARACTERISTICS:

Optilith™ 1486 A is an easy-to-disperse, low viscosity solution. **Optilith 1486 A** maximizes “stay open” time in sheetfed and heatset inks with minimum effect on drying time. Recommended usage of **Optilith 1486 A** in lithographic inks is 0.7-1.5%.

APPLICATIONS:

- Heatset offset ink
- Sheetfed offset ink

BENEFITS:

- Maximum ink “stay open” time
- Minimum effect on drying time
- Anti-skinning
- Pumpable for easy transfer and dispersion

Typical Properties

Property	Value	Test Method / Standard
Appearance:	Amber solution	
Viscosity:	130	GH Bubble Tube @ 25°C, E-E (sec.) Method: BAX-QC-106
Inkometer Tack:	5.5	400 rpm, 30 sec. @ 90°F Method PP-QC-101
% Non-volatile:	49	Method: BAX-QC-195
Solvent Boiling Range:	464-536°F	
Weight/Gallon:	7.1 lbs.	Method: BAX-QC-130

Updated 05/28/2015 JGC

For more information, please contact your sales or technical representative.

® and ™ Licensed trademarks of Lawter, Inc.

DISCLAIMER

The information provided herein was believed by Lawter, Inc. (“Lawter”) to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product, and to determine the suitability of the product for its intended use. All products supplied by Lawter are subject to Lawter’s terms and conditions of sale. LAWTER MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY LAWTER, except that the product shall conform to Lawter’s specifications. Nothing contained herein constitutes an offer for the sale of any product.