



Technical Data Sheet

Setaprint™ 150 A Phenolic Modified Rosin Ester

IMPORTANT CHARACTERISTICS:

Setaprint™ 150 A is a **Lawter™** phenolic modified rosin ester. **Setaprint 150 A** is a unique ultra-high molecular weight resin, possessing high viscosity while maintaining a workable dilution range.

Setaprint 150 A provides greater compatibility with drying oils and alkyds than ever achieved before at this viscosity. These combined properties allow **Setaprint 150A** to help improve gloss, transfer, dot sharpness, gel structure and press stability. This resin provides an inner structure in solution allowing for reduction in gelling agents and improved stability of gelled systems.

APPLICATIONS:

- Heatset gel vehicles
- Sheetfed gel vehicles
- Gloss varnishes
- Overprint varnishes

BENEFITS:

- Low solubility, high gloss and extremely fast setting
- Stable rheology under high shear conditions and very good press stability
- Good water balance and holdout, no misting
- High melt point and heat resistance

Typical Properties

Properties	Value	Test Method / Standard
Color:	11	60% in Xylene BAX-QC-103
Acid Value:	24	BAX-QC-102
Viscosity @ 2.5s	470	48% Resin in TXIB TA Rheometer Method: BAX-QC-132
Tan Delta	2.80	48% Resin in TXIB TA Rheometer Method: BAX-QC-132
Cloud Point	140°C	10% PKWF 6/9 Test Oil*

*Registered Trademark of Haltermann's Oils

Updated 5/18/2015 DH

For more information, please contact your sales or technical representative.

® and ™ Licensed trademarks of Lawter, Inc.

DISCLAIMER

The information provided herein was believed by Lawter, Inc. ("Lawter") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product, and to determine the suitability of the product for its intended use. All products supplied by Lawter are subject to Lawter's terms and conditions of sale. LAWTER MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY LAWTER, except that the product shall conform to Lawter's specifications. Nothing contained herein constitutes an offer for the sale of any product.