



Technical Data Sheet

Setaprint™ 2244 A Phenolic Modified Rosin Ester

IMPORTANT CHARACTERISTICS:

Setaprint™ 2244 A is a relatively low solubility, high viscosity resin which exhibits excellent solvent release for fast setting and good holdout. **Setaprint 2244 A** has excellent compatibility with drying oils and gives varnishes a hard, scuff resistant surface. **Setaprint 2244 A** is specially formulated to be free of bisphenol A.

APPLICATIONS:

- Offset inks
- Coatings

BENEFITS:

- High viscosity
- Fast setting
- Scuff resistant

Typical Properties

Property	Value	Test Method / Standard
Melt Point:	166°C	Ring & Ball BAX-QC-100
Acid Value:	24	BAX-QC-102
Viscosity:	465	1:2 ARLO, Line:Line @25°C, sec. BAX-QC-107A
Cloud Point:	145°C	10% PKWF™ 6/9 Test Oil** BAX-QC-196

**Registered Trademark of Haltermann Products

Updated 5/18/2015 DH

For more information, please contact your sales or technical representative.

® and ™ Licensed trademarks of Lawter, Inc.

DISCLAIMER

The information provided herein was believed by Lawter, Inc. ("Lawter") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product, and to determine the suitability of the product for its intended use. All products supplied by Lawter are subject to Lawter's terms and conditions of sale. LAWTER MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY LAWTER, except that the product shall conform to Lawter's specifications. Nothing contained herein constitutes an offer for the sale of any product.