

Setaprint[™] 7502 A Phenolic Modified Rosin Ester

IMPORTANT CHARACTERISTICS:

Setaprint™ 7502 A is a high viscosity, high molecular weight phenolic modified rosin resin exhibiting a high tolerance for low KB ink oils. The high viscosity of Setaprint 7502 A improves lithographic performance when modifying less soluble resin systems. A unique blend of viscosity and aliphatic solubility, combined with excellent compatibility with drying oils makes Setaprint 7502 A ideal for high speed, high performance ink vehicles.

APPLICATIONS:

- Offset inks
- Coatings

BENEFITS:

- High viscosity
- High speed/high performance

Typical Properties

Property	Value	Test Method / Standard
Melt Point:	174℃	Ring & Ball BAX-QC-100
Acid Value:	24	BAX-QC-102
Viscosity at 2.5s ⁻¹ :	725	48% Resin in TXIB
		TA Rheometer Method: BAX-QC-132
Tan Delta:	2.70	48% Resin in TXIB
		TA Rheometer Method: BAX-QC-132
Cloud Point:	130℃	10% PKWF™ Magiesol™ 47*
		BAX-QC-196
Color	9	BAX-QC-103

^{*}Registered Trademark of Calumet Specialty Products Partners, LP.

Updated 5/18/2015 DH

For more information, please contact your sales or technical representative.

® and ™ Licensed trademarks of Lawter, Inc.

DISCLAIMER

The information provided herein was believed by Lawter, Inc. ("Lawter") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product, and to determine the suitability of the product for its intended use. All products supplied by Lawter are subject to Lawter's terms and conditions of sale. LAWTER MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY LAWTER, except that the product shall conform to Lawter's specifications. Nothing contained herein constitutes an offer for the sale of any product.