

Ultrafine™ 1000 A Micronized Polyethylene Wax

IMPORTANT CHARACTERISTICS:

Ultrafine™ 1000 A is a finely micronized polyethylene wax powder recommended when maximum rub and mar resistance, block resistance, slip, re-coatability and elevated processing temperatures are required.

The average particle size of **Ultrafine 1000 A** is 7 microns with a narrow distribution of particle sizes for ease of dispersion and uniformity during processing. Addition levels range from 0.5 to 3%, depending upon application requirements.

APPLICATIONS:

- Solvent-based and water-based flexographic and gravure Ink
- Sheetfed, UV & metal deco
- Coil, can, wood and powder coatings, solvent-based stains and lacquers

BENEFITS:

- Maximum rub and mar resistance, block resistance, slip and re-coatability
- Narrow particle size distribution for ease of dispersion and uniformity
- Tolerable of higher processing temperatures

Typical Properties

Property	Value	Test Method / Standard
Grind:	N-2	NPIRI Gage Units (20% in oil) Method: BAX-QC-201
Softening Point:	235-245°F	Method: ASTM D36
Average Particle Size:	7 microns	Malvern Analyzer, microns
Specific Gravity:	0.95	

Updated 5/12/2015 JGC

For more information, please contact your sales or technical representative.

® and ™ Licensed trademarks of Lawter, Inc.

DISCLAIMER

The information provided herein was believed by Lawter, Inc. ("Lawter") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product, and to determine the suitability of the product for its intended use. All products supplied by Lawter are subject to Lawter's terms and conditions of sale. LAWTER MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY LAWTER, except that the product shall conform to Lawter's specifications. Nothing contained herein constitutes an offer for the sale of any product.