

REACTOL™ 1719H C

REACTOL™ 1719H C is a very high softening point Ketonic resin that offers good gloss, adhesion & pigment wetting properties. It is characterized by its rapid solubility.

REACTOL™ 1719H C offers fast solvent release of the polyketone family of resins.

Application

Flexographic inks, Paper coatings, Laminating inks, Primer coatings, Heat-seal coatings, wood primers, Ball-point pen ink

- ▲ Alcohol Solubility
- ▲ Soluble in wide range of solvents
- ▲ Heat resistance
- ▲ Gasoline resistance
- ▲ Excellent compatibility with most resin systems
- ▲ Low colour

Typical properties

Property	Value	Unit	Test Method
Acid value	<1	mgKOH/g	Titration
Melting point	155	°C	Ring & Ball method
Viscosity @30°C (50% in Ethanol)	25	seconds	Ford 4 cup

Updated December 30, 2024 by JH

Packaging

REACTOL™ 1719H C is shipped in 25 kg bags.

Shelf life and storage conditions

Shelf life from date of production is typically 6 months. The resin should be stored at temperatures below 30°C. If the resin is stored wrongly or for a longer period of time, an increase in viscosity and color is possible.

® and ™ Licensed trademarks of Lawter, Inc.

Disclaimer

The information provided herein was believed by Lawter, Inc. ("Lawter") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product, and to determine the suitability of the product for its intended use. All products supplied by Lawter are subject to Lawter's terms and conditions of sale. LAWTER MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY LAWTER, except that the product shall conform to Lawter's specifications. Nothing contained herein constitutes an offer for the sale of any product.