

## REACTOL™ UV-2050R C

REACTOL™ UV-2050R C is a polyester resin used in UV ink with good balance between curing(reactivity) and adhesion. It can be used in various substrates such as paper and films(PET, PE).

### Application

UV Offset ink, UV ink

▲ Substrates of Paper, PET and PE

▲ Balance of curing and adhesion

### Typical properties

Property	Value	Unit	Test Method
Acid value	20	mgKOH/g	JIS K 0070
Color	6		Gardner
Softening point	110	°C	Ring and Ball

Updated May 20, 2025 by XH

### Packaging

REACTOL™ UV-2050R C is available in 20 kg bags.

### Shelf life and storage conditions

Shelf life from date of production is typically 12 months. The resin should be stored at cool and dark place with temperature under 30°C.

If it is stored wrongly or for a longer period of time, a change on product quality is possible.

® and ™ Licensed trademarks of Lawter, Inc.

#### Disclaimer

The information provided herein was believed by Lawter, Inc. ("Lawter") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product, and to determine the suitability of the product for its intended use. All products supplied by Lawter are subject to Lawter's terms and conditions of sale.

LAWTER MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY LAWTER, except that the product shall conform to Lawter's specifications. Nothing contained herein constitutes an offer for the sale of any product.