

## ULTRAPOLY™ 210 A

**ULTRAPOLY™ 210 A** is a high performance blend of tough, low COF polyethylene dispersed in a hard-drying binder. **ULTRAPOLY™ 210 A** is recommended where abrasion, mar resistance, and slip are required. **ULTRAPOLY™ 210 A** is 100% non-volatile and fast-setting. It protects the film in the earliest stages of the printing process while developing exceptional toughness over time. **ULTRAPOLY™ 210 A** is coatable and may be used for laser work when combined with PTFE. For optimum heat resistance, we recommend using 3 parts **ULTRAPOLY™ 210 A** to 1 part **FLUORON™ 735 A** (a PTFE concentrate). Recommended use level is 4 to 6%.

### Applications

Sheetfed offset ink. OPV, metal decorating, UV inks. Aqueous & UV coatable, and hot foil stampable.

- ▲ Excellent abrasion and mar resistance
- ▲ Fast-setting, hard-drying vehicle
- ▲ Enhances lubricity without PTFE

### Typical properties

Property	Value	Unit	Test Method
Grind (10 % in ink)	N-0	-	NPIRI Gage units, BAX-QC-201
Peppering (10 % in ink)	N-5	-	NPIRI Gage units, BAX-QC-201
Color	Light yellow	-	Compared to standard
Body	Creamy paste	-	Compared to standard
Bio-Renewable Content, (+/-2%)	58	wt%	Theoretical value based on formulation

Updated March 7, 2025 by AH

### Packaging

ULTRAPOLY™ 210 A is shipped in 350 lb drums.

### Shelf life and storage conditions

When stored properly, shelf life from date of production is approximately 12 months. The product should be stored at temperatures ideally between 10 and 30°C (50-86°F). The packaging should be kept tightly closed and stored in dry conditions. An increase in viscosity or skinning is possible if the wax compound is stored in wrong conditions or left exposed to air for an extended period of time.

**Product carbon footprint** calculated in line with ISO14040 standard is available upon request.

® and ™ Licensed trademarks of Lawter, Inc.

#### Disclaimer

The information provided herein was believed by Lawter, Inc. ("Lawter") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product, and to determine the suitability of the product for its intended use. All products supplied by Lawter are subject to Lawter's terms and conditions of sale. LAWTER MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY LAWTER, except that the product shall conform to Lawter's specifications. Nothing contained herein constitutes an offer for the sale of any product.