

SETALIN™ V 409 E

SETALIN™ V 409 E is a sunflower oil based alkyd resin with low-yellowing properties, making this alkyd resin particularly suitable for low odour inks, white inks and low-yellowing over print varnishes (OPV).

This alkyd resin can also be very suitable for 3-piece can metal decorating inks (whites).

Application

Offset, sheetfed, metal deco inks (3-piece can, whites), low odour inks, low yellowing inks, over print varnishes (OPV).

- ▲ Low yellowing
- ▲ High Gloss
- ▲ Recommended using Ce/Zr driers
- ▲ Low odour
- ▲ Good pigment wetting
- ▲ Tin free

Typical properties

Property	Value	Unit	Test Method
Viscosity	72	Pa.s	Physica 23 °C, at 25 sec ⁻¹ , LIMV2
Colour	6	Gardner	LIMA5
Acid Value	8	mg KOH/g	LIMA1
Methanol number	45	ml per 5 g alkyd solution	LIMA2
Oil length	60	%	Calculation
Appearance	Slight haze		Visual

Updated January 3, 2025 by SA

Packaging

SETALIN™ V 409 E is available in drums (190 kg).

Shelf life and storage conditions

Shelf life from date of production is typically 24 months. The resin should be stored at temperatures between 10 and 30°C. The packaging should be kept tightly closed and stored in dry conditions.

Product carbon footprint calculated in line with ISO14040 standard is available upon request.

® and ™ Licensed trademarks of Lawter, Inc.

Disclaimer

The information provided herein was believed by Lawter, Inc. ("Lawter") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product, and to determine the suitability of the product for its intended use. All products supplied by Lawter are subject to Lawter's terms and conditions of sale. LAWTER MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY LAWTER, except that the product shall conform to Lawter's specifications. Nothing contained herein constitutes an offer for the sale of any product.