

## SETALIN™ B 1700

SETALIN™ B 1700 is a vehicle with 80% non-volatiles, based on a rosin resin esterified with glycerin, modified with alkylphenol.

SETALIN™ B 1700 is a sheetfed vehicle for standard applications with a good water behaviour and very good flow.

### Application

Sheetfed offset inks

- ▲ Low misting
- ▲ Very good gloss

- ▲ Very good water balance properties
- ▲ Excellent pigment wetting

### Typical properties

Property	Value	Unit	Test Method
Viscosity	45	Poise	Physica, C&P 30°C, 25s <sup>-1</sup>
Dilutability	20	ml	ml M47 / 10 g
Sustainability			
Bio-Renewable Content	69	%	Mass ratio

Updated February 27, 2025 by MA

### Packaging

SETALIN™ B 1700 can be available in drums.

### Shelf life and storage conditions

Shelf life from date of production is typically 12 months.

The varnish should be stored at temperatures ideally between 10 and 30°C. The packaging should be kept tightly closed and stored in dry conditions.

An increase in viscosity is possible if the varnish is stored in wrong conditions or for an extended period of time.

® and ™ Licensed trademarks of Lawter, Inc.

#### Disclaimer

The information provided herein was believed by Lawter, Inc. ("Lawter") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product, and to determine the suitability of the product for its intended use. All products supplied by Lawter are subject to Lawter's terms and conditions of sale.

LAWTER MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY LAWTER, except that the product shall conform to Lawter's specifications. Nothing contained herein constitutes an offer for the sale of any product.